



Blendex S12/20

Use within 12 months from production date
(unopened and in the original packaging).

Description

BLENDEX S12 20 is a thermoplastic polyurethane in methyl-ethyl-ketone solution, with a transparent yellowish appearance. Dry density of 1,2 g/cm³.

Application

BLENDEX S12 20 is used as soft heat sealable adhesive for lamination of various products, like PU, PVC, TR, leather, synthetic leather and fabrics.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	20±1
3. Brookfield Viscosity 25°C	mPa.s	2000 - 6000 ⁽¹⁾
95. Heat Sealability Solvents	°C	> 70 MEK

⁽¹⁾ N. 4 RV; 20 RPM

Handling

Reactivation temperature: over 70°C.
After reactivation, the product has good adhesive properties for a quite long time (open time: long).

Packaging

The product is supplied in iron drums (170 kg).

Storing

Stir well before use. Keep containers well closed to prevent solvent evaporation. Store at temperatures between + 5 and + 30°C, far from heat sources and direct sunlight.