



Solacril 204

(Provisional)

Description

SOLACRIL 204 is a solvent based acrylic PSA, with a very good resistance to ageing, light and heat.

Application

SOLACRIL 204 can be applied on various substrates: paper, polyester, PP, PE, PVC, etc. It is particularly suitable for protective films.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	50±1
3. Brookfield Viscosity 25°C Solvents	mPa.s	2000 - 4000 ⁽¹⁾ hexane / toluene

⁽¹⁾ N. 4 RV; 20 RPM

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	700
17. Rolling Ball Tack	cm	3

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm

Handling

SOLACRIL 204 must be activated before use, to increase adhesion to plastic films and to improve cohesion.

Suggested activators are: CURING AGENT CH or CURING AGENT D, recommended concentration is 0.5 - 1%. After activation, pot-life is reduced, as

the crosslinking mechanism starts immediately after the addition of the crosslinker.

Packaging

The product is supplied in iron drums (180 kg).

Storing

Product must be stored at temperatures between +5°C and +40°C. Keep the containers well closed to avoid solvent evaporation.

Use within 6 months from production date (unopened and in the original packaging).