ichemco
Developing Chemical Excellence

member of Afera

CERTIFIED MANAGEMENT SYSTEMS
CERTIQUALITY
UNI EN ISO **9001:2015**
UNI EN ISO **14001:2015**
UNI ISO **45001:2018**

PRIMER PP 11

(Provisional)

Description

PRIMER PP 11 is a solvent-based primer for polyolefin films and natural rubber-based adhesives.

Application

PRIMER PP 11 has been developed for application to treated polyolefin films.

Technical Specifications

Method of analysis	UoM	Standard
1. Total Solids	%	10 ± 0.5
Solvents		toluene

Handling

Application systems can be reverse-roll or Mayer bar.
PRIMER PP 11 must be activated before use by adding 1–1.5% of CURING AGENT D, the pot-life of the product is reduced as crosslinking starts immediately after addition of the curing agent.
Stir well after activation. Apply 0.5–0.6 g dry/ sqm.
If necessary, the product can be diluted with toluene.

Packaging

The product is supplied in iron drums (180 kg).

Storing

Store the product at room temperature, protected from direct sunlight and humidity. Stir well before use.

Use within 12 months from production date (unopened and in the original packaging).

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 15 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it